

## Roof Product List

List Current as of February 1, 2008

\*As of December 31, 2007, all new ENERGY STAR qualified products are prohibited from being cleaned during testing.

\*\*Warranty does not necessarily cover solar reflectance.

Company Name	Brand	Model	Type	Initial Solar Reflectance	Solar Reflectance after 3 years	Initial Emissivity	Low Slope?	Steep Slope?	Roof Cleaned Prior to 3rd Year Test	Warranty Period (years)	Date Qualified
Acrylux Paint Manufacturing Co. Inc.	Acrylux	Roof Mastic	Coating	0.87	0.66	0.89	Y	Y	No	5	1/25/08
Acrymax Technologies, Inc.	Acrymax	AF-130	Coating	0.85	0.75	0.9	Y	Y		5 - 10	
Adurel International Inc.	Adurel	A808	Coating	0.84	0.66	0.88	Y	Y	No	5	10/26/07
Adurel International Inc.	Adurel	MS2200	Coating	0.8	0.73	0.88	Y	Y	No	5	10/26/07
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex	Coating	0.89	0.85	0.89	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex: Urethane	Coating	0.88	0.84	0.88	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex: Ceramic	Coating	0.88	0.84	0.89	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex: Hydro	Coating	0.91	0.87	0.88	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Flex: Sub Zero	Coating	0.9	0.83	0.89	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Kool	Coating	0.88	0.82	0.88	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield	Coating	0.88	0.84	0.89	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield: Ceramic	Coating	0.89	0.82	0.89	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield: F.R.C.	Coating	0.86	0.82	0.88	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield: Sub Zero	Coating	0.88	0.84	0.89	Y	Y		10	
Advanced Coating Systems, Inc.	Energy Seal Coatings	Acu-Shield: Urethane	Coating	0.88	0.84	0.88	Y	Y		10	
AEP-SPAN	Bare	Cap, High, Snap, Span Seam - Bare Metal	Metal	0.78	0.58	0.06	Y	Y		20	

Company Name	Brand	Model	Type	Initial Solar Reflectance	Solar Reflectance after 3 years	Initial Emissivity	Low Slope?	Steep Slope?	Roof Cleaned Prior to 3rd Year Test	Warranty Period (years)	Date Qualified
AEP-SPAN	Bare	Flush Panel - Bare Metal	Metal	0.78	0.58	0.06	Y	Y		20	
AEP-SPAN	Bare	Span Lok - Bare Metal	Metal	0.78	0.58	0.06	Y	Y		20	
AEP-SPAN	Cool Antique Patina	DuraTech 5000	Metal	0.28	0.28	0.86	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Ash Gray	DuraTech 5000	Metal	0.38	0.37	0.88	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Copper Penny	DuraTech 5000	Metal	0.4	0.42	0.86	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Jade Green	DuraTech 5000	Metal	0.26	0.26	0.89	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Marine Green	DuraTech 5000	Metal	0.31	0.31	0.88	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Metallic Champagne	DuraTech 5000	Metal	0.38	0.39	0.87	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Parchment	DuraTech 5000	Metal	0.33	0.35	0.89	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Sierra Tan	DuraTech 5000	Metal	0.34	0.38	0.88	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Silver	DuraTech 5000	Metal	0.47	0.47	0.86	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Tahoe Blue	DuraTech 5000	Metal	0.28	0.25	0.85	N	Y	Yes	20	10/25/06
AEP-SPAN	Cool Weathered Copper	DuraTech 5000	Metal	0.27	0.28	0.88	N	Y	Yes	20	10/25/06
AEP-SPAN	Snowdrift White	DuraTech 5000	Metal	0.56	0.56	0.88	N	Y	Yes	20	10/25/06
Agway Metals Inc.	04/01/0150	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08
Agway Metals Inc.	7-150F	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08
Agway Metals Inc.	7-150NF	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08
Agway Metals Inc.	7/8 Corrugated	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08
Agway Metals Inc.	08/01/0175	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08
Agway Metals Inc.	AR-38 Standing Seam	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08
Agway Metals Inc.	AR-50 Standing Seam	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08

Company Name	Brand	Model	Type	Initial Solar Reflectance	Solar Reflectance after 3 years	Initial Emissivity	Low Slope?	Steep Slope?	Roof Cleaned Prior to 3rd Year Test	Warranty Period (years)	Date Qualified
Agway Metals Inc.	Century Rib	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08
Agway Metals Inc.	Springhouse Shingles	Galvalume Plus	Metal	0.67	0.58	0.12	Y	Y	No	25	1/7/08
Akzo Nobel Coatings	CERAM-A-STAR 1050	KH	Coating	0.55	0.55	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	821-35W018-511	Coating	0.47	0.46	0.86	N	Y	No	10	9/13/05
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XA3G41335	Coating	0.39	0.38	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XA3Y41357	Coating	0.39	0.38	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XA3Y41601	Coating	0.3	0.3	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XA5G41220	Coating	0.37	0.35	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XG3G40889	Coating	0.29	0.28	0.86	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XG3G41345	Coating	0.28	0.28	0.87	N	Y	No	40	2/28/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XG3Y42033	Coating	0.34	0.34	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G40855	Coating	0.54	0.51	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G40861	Coating	0.5	0.48	0.88	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41211	Coating	0.52	0.51	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41213	Coating	0.6	0.58	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41216	Coating	0.33	0.32	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41332	Coating	0.52	0.52	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41893	Coating	0.58	0.6	0.87	N	Y	No	40	11/17/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3G41894	Coating	0.51	0.51	0.88	N	Y	No	40	11/17/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3Y41142A	Coating	0.48	0.46	0.87	N	Y	No	40	11/16/06

Company Name	Brand	Model	Type	Initial Solar Reflectance	Solar Reflectance after 3 years	Initial Emissivity	Low Slope?	Steep Slope?	Roof Cleaned Prior to 3rd Year Test	Warranty Period (years)	Date Qualified
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3Y41371	Coating	0.48	0.47	0.86	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3Y41600	Coating	0.55	0.5	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XH3Y41653	Coating	0.28	0.29	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XL3Y41136A	Coating	0.26	0.26	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G40857	Coating	0.35	0.42	0.88	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G40864	Coating	0.3	0.33	0.86	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G41331	Coating	0.32	0.32	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G41711	Coating	0.35	0.35	0.87	N	Y	No	40	2/28/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3G41881	Coating	0.35	0.35	0.87	N	Y	No	40	11/17/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3Y41364	Coating	0.3	0.3	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3Y41366	Coating	0.32	0.32	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR3Y42037	Coating	0.32	0.32	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XR5G41223	Coating	0.32	0.32	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XT3G41215	Coating	0.36	0.36	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G40863	Coating	0.58	0.54	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G41212	Coating	0.65	0.63	0.87	Y	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G41214	Coating	0.56	0.46	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G41328	Coating	0.57	0.54	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3G41885	Coating	0.61	0.61	0.87	N	Y	No	40	11/17/06

Company Name	Brand	Model	Type	Initial Solar Reflectance	Solar Reflectance after 3 years	Initial Emissivity	Low Slope?	Steep Slope?	Roof Cleaned Prior to 3rd Year Test	Warranty Period (years)	Date Qualified
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3Y41356	Coating	0.51	0.52	0.88	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3Y41374	Coating	0.58	0.54	0.87	N	Y	No	40	11/16/06
Akzo Nobel Coatings	CERAM-A-STAR® 1050	XW3Y42034	Coating	0.57	0.54	0.87	N	Y	No	40	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 900	SA3X33318	Coating	0.35	0.35	0.88	N	Y	No	25	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 900	SH3X30570	Coating	0.59	0.57	0.87	N	Y	No	25	11/17/06
Akzo Nobel Coatings	CERAM-A-STAR® 900	SH3X31581	Coating	0.51	0.49	0.87	N	Y	No	25	11/17/06
Akzo Nobel Coatings	CERAM-A-STAR® 900	SL3X32940 Harbor Blue	Coating	0.32	0.32	0.87	N	Y	No	25	9/14/05
Akzo Nobel Coatings	CERAM-A-STAR® 900	ST3X30571	Coating	0.36	0.37	0.87	N	Y	No	25	11/17/06
Akzo Nobel Coatings	CERAM-A-STAR® 900	SW3X24009	Coating	0.55	0.46	0.87	N	Y	No	20	3/10/04
Akzo Nobel Coatings	CERAM-A-STAR® 900	SW3X31091	Coating	0.64	0.6	0.86	N	Y	No	25	11/17/06
Akzo Nobel Coatings	CERAM-A-STAR® 900	SW3X32695	Coating	0.6	0.6	0.86	N	Y	No	25	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 940	SR3P24003	Coating	0.41	0.41	0.87	N	Y	No	25	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 940	SR3P24003 Crimson Red	Coating	0.39	0.39	0.87	N	Y	No	25	9/14/05
Akzo Nobel Coatings	CERAM-A-STAR® 940	SR3P32680	Coating	0.4	0.4	0.87	N	Y	No	25	2/16/07
Akzo Nobel Coatings	CERAM-A-STAR® 940	SR5P24847 Red	Coating	0.31	0.31	0.86	N	Y	No	20	3/10/04
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-30W018-214 Light Gray	Coating	0.27	0.28	0.87	N	Y	No	30	9/14/05
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-30W018-98 White	Coating	0.62	0.51	0.87	N	Y	No	30	9/14/05
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-35A018-116 Light Blue	Coating	0.26	0.26	0.88	N	Y	No	30	9/14/05
Akzo Nobel Coatings	CERAM-A-STAR® 950	828-35D018-221A Sandstone	Coating	0.57	0.45	0.87	N	Y	No	30	11/4/05



















































































































































































